

**AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

**LISTING OF CLAIMS:**

1. (previously presented): A pressure sensitive adhesive product comprising a support obtained by applying a pressure sensitive adhesive composition which comprises the following components (A), (B) and (C) to the support and thermally curing the pressure sensitive adhesive composition:
  - (A) a hydrolyzable silyl group-containing organic polymer containing at least 1.3 hydrolyzable silyl groups per molecule and having a number average molecular weight of 20,000 to 50,000, the main chain of the organic polymer being substantially composed of a repeating unit or units represented by the general formula -R<sup>1</sup>-O- (R<sup>1</sup> being a divalent alkylene group);
  - (B) a hydrolyzable silyl group-containing organic polymer containing 0.3 to 1.3 hydrolyzable silyl groups per molecule and having a number average molecular weight of 3,000 to 10,000, a compounding ratio of which is 1 to 100 parts by weight relative to 100 parts by weight of (A), and the main chain of which polymer being substantially composed of a repeating unit or units represented by the general formula -R<sup>1</sup>-O- (R<sup>1</sup> being a divalent alkylene group);
  - (C) a tackifier resin selected from the group consisting of terpene resins, terpene phenol resins, petroleum resins, rosin ester resins, and admixtures thereof, and a compounding ratio of which is 30 to 100 parts by weight, relative to a combined total of 100 parts by weight of (A) and (B).

2. (canceled).

3. (previously presented): The pressure sensitive adhesive product according to

Claim 1

wherein the main chain of the hydrolyzable silyl group-containing organic polymers (A) and (B) is substantially polyoxypropylene.

4. (previously presented): The pressure sensitive adhesive product according to

Claim 1

wherein the hydrolyzable silyl group of the hydrolyzable silyl group-containing organic polymers (A) and (B) is represented by the following general formula (I):



(wherein, R<sup>2</sup> represents a substituted or unsubstituted monovalent organic group containing 1 to 20 carbon atoms, X represents a hydrolyzable group, and a represents 1, 2 or 3).

5-6. (canceled).

7. (previously presented): The pressure sensitive adhesive product according to

Claim 3

wherein the hydrolyzable silyl group of the hydrolyzable silyl group-containing organic polymers (A) and (B) is represented by the following general formula (I):



(wherein, R<sup>2</sup> represents a substituted or unsubstituted monovalent organic group containing 1 to 20 carbon atoms, X represents a hydrolyzable group, and a represents 1, 2 or 3).

8. (canceled).

9. (previously presented): The pressure sensitive adhesive product according to Claim 1, wherein the support is at least one selected from the group consisting of synthetic resin films, modified natural films, paper, cloth and metal foils.

10. (previously presented): The pressure sensitive adhesive product according to Claim 1, wherein the pressure sensitive adhesive composition is cured at a temperature of 50° to 180° for 1 minute to 1 hour.

11. (new): The pressure sensitive adhesive product according to Claim 1, which is selected from the group consisting of pressure sensitive adhesive tapes, pressure sensitive adhesive sheets, pressure sensitive adhesive films and pressure sensitive adhesive labels.